



RENOFIX 12

THOROUGH PROCESSING MATERIAL

Please follow the technical instructions!

AREA OF APPLICATION:

Dry mortar prefabricated according to EN 998-1. Mineral, environmentally-free and high-quality clean mortar for thorough processing of walls and ceilings. Used for facades and interior surfaces as final plastering layer in order to achieve smooth final surface.

COMPOSITION:

- White cement
- Lime
- Fine lime sand

FEATURES:

- Well processed
- High level of vapour resistance

BASE PREPARATION:

The base must be dry and clean (without sheath oils and waste).

MORTAR PREPARATION:

If prepared manually, mix one bag of Renofix 12 with hand mixer or mortar machine Skure-Tech S4 with 6.5-7 litres of clean water until the mass becomes homogenous and lump-free. After 10 minutes stir once again. Use the material within 2 hours.

PROCESSING AND PROCESSING CONDITIONS:

The material is applied with a trowel and smoothed with foamed tool. The minimum thickness for mortar layer is from 3 mm to 5 mm. **It must not be used at temperatures lower than +5°C.** It is not to be mixed with other materials.



WARNING:

Contains lime. Irritates the skin and the eyes. In case of skin or contact, rinse with clean water, and in case of contact with the eyes, seek medical assistance.

DELIVERY:

Delivered in 25 kg paper bags protected against moisture.



STORAGE:

To be stored in dry space, on top of wooden pallets. Storage time – 6 months.

Technical data :	
Product code:	5319990620088
Product code:	1012
Bags on a pallet:	42
Unit quantity:	25 kg / EH
Granulation:	0,6 mm
Amount of water required:	6,5-7 l. / bag
Minimum layer thickness:	3-5 mm
Consumption:	1,0 kg per m ² is needed for thickness of 1 mm

RENOFIX 12

Note:	Consumption figures are approximate and depend to a large extent on the base and installation method
Period of use:	2 hours
Material density, if dry (EN 1015-10):	1400 kg/m ³
Hardness under pressure for 28 days (EN 1015-11):	3,3 N/mm ²
MG (EN 998-1):	GP CSII W0
Colour:	GREY

General instructions:



All data about the material cease to be valid following the issuance of the above list. These are the data resulting from our current analyses. No legal obligation may arise from these data. The RENOVA products, as well as all raw materials contained in them are subject to constant, continuous tests to ensure constant and same level quality. Our technical advisers are at your disposal for any inquiries regarding the application, processing, and presentation of our products. You may find our current data at www.renova.com.mk, as a document or ask for them in the retail shops.



RENOVA PUTZ | www.renova.com.mk

RENOVA Xep-ite, Tetovo, Makedonija | Tel.: 044 487 300 | Fax: 044 487 200 | info@renova.com.mk
RENOVA Gureza, Uroševac, Kosovo | Tel.: 00381 290 323 311 | Fax: 00381 290 396 396 | renova_ferizaj@hotmail.com
RENOVA Vore, Tirana, Albanija | Tel.: 00355 48 301 909 | Fax: 00355 48 301 908 | renova.tirana@hotmail.com